



Blake





Blake

Blake is a flatwoven quality, which is in the Textaafoam Performance Collection.

This collection consists only of fabrics that pass the highest standards in durability and maintenance. They are long lasting, easy to clean and suitable for almost every type of upholstery.

Due to an extra finish Blake passes the BS5852 cigarette (ignition source 0) & match (ignition source 1) and the EN1021 cigarette (part 1) & match (part 2).

Blake is durable and strong and has a light woolly look & feel due to a needle punch coating. It is yarn dyed and therefore it has a very stable colour consistency. The finish creates this dull and woolly aspect. Available from stock in a wide range of trendy and commercial colours, Blake is a good choice for all different types of furniture.

Textaafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 100%PES
/ backside n/a
/ polyester flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



beige 05 (fr)




blush 92 (fr)




brown 15 (fr)




chocolate 17 (fr)




clay 84 (fr)




denim 153 (fr)



darkgrey 68 (fr)



emerald 184 (fr)




graphite 66 (fr)



grey 65 (fr)



lightgrey 60 (fr)



liver 10 (fr)


Please note: colours may vary according to your screen settings.



maize 22 (fr)



mocca 13 (fr)




natural 01 (fr)



navy 49 (fr)




olive 53 (fr)




petrol 56 (fr)



red 35 (fr)



sky 142 (fr)



taupe 12 (fr)



winered 39 (fr)

Please note: colours may vary according to your screen settings.

Blake - Article passport

Multi-coloured strong fabric with woolly aspect. Typical everyone's friend and suitable for various purposes.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	polyester flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100%PES
Composition backside	n/a
Coating	needle punch
Statistic code	54079300
Dyeing method	yarn dyed
Available colours	22
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	Centexbel		passed				
	DIN EN ISO 1021-2:2014. Source: smouldering cigarette	Centexbel		passed				
	Ignitability (match test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 5 part 1 Ignition source 1: match flame equivalent	Centexbel		passed			
DIN EN ISO 1021-1:2014. Source: match flame equivalent		Centexbel		passed				






Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 50
Material weight in grams per linear meter	± 442

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	798	1.344	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	79,8	140,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,5	3,1	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	n/a	n/a	n/a	n/a	n/a



Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl