



# Dexter





# Dexter

Meet Dexter. A flatwoven polyester quality with a matte and woolly look from our Textafoam Comfort Collection. A collection that consists only of soft, voluminous and elegant fabrics.

Dexter is optimal resistant to moisture and also easy to clean and maintain. This luxurious piece dyed textile has been finished with a damp and dirt prevented treatment and also washable at 30 degrees (machine wash).

Woven on a dobby loom and suitable for all kind of upholstery, even perfect for drapery. During use a certain wooliness or hairiness can appear, this has no influence on the durability of this fabric.

Available from stock in commercial and deep colours.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

## Composition

/ faceside 100% PES  
/ backside n/a  
/ flatweave

## Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery




beige 05



coral 95



darkgrey 68



ecru 102



forest 162



graphite 66



grey 65



hazel 96



moss 59



mustard 06




royalblue 47



scarlet 141

Please note: colours may vary according to your screen settings.



slate 87



taupe 12



wenge 192

Please note: colours may vary according to your screen settings.

## Dexter - Article passport

A luxurious flatwoven polyester quality with a matte and woolly look.

Available from stock in a wide range of contemporary and commercial colours.

### Product characteristics

Productgroup	flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Composition backside	n/a
Bonding / Coating	n/a
Statistic code	54075200
Dyeing method	piece dyed
Available colours	15
Packaging	bubble wrap

### Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	28.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4-5		min. 4	min.5	B-C
	middle colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
dark colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A	
	ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL	passed				



### Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 35
Material weight in grams per linear meter	± 636

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.584	1.581	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	123,1	171,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

### Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.



Textafoam b.v.  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@textafoam.nl  
www.textafoam.nl