River



Textaafoam | Skins
Expect what's next in furniture fabrics

River

The Textaafoam Skins Collection contains all kinds of leather alternatives. River is a well running article in this Collection, so new colours have been developed.

The backing has a very thick and heavy fleece which gives a nice and full hand feel. For the top layer we used a woven micro suede with a nice leather print. River is available in 21 contemporary and fresh colours.

Furthermore, River is easy to clean and maintain. This article is treated to be damp and dirt repellent. During daily use, the used aspect of this fabric will become more visible. This will not influence the quality or durability in any way.

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

Textaafoam originals *Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%PES
/ microsuede woven

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



brandy 127



brown 15



burgundy 34



camel 09



cognac 28



desert 109



darkgrey 68



espresso 123



eucalyptus 193



forest 162



graphite 66



hazel 96

Please note: colours may vary according to your screen settings.



liver 10



mocca 13



mustard 06



natural 01



plumb 168



steel 149



taupe 12



thyme 206



turtle 88

Please note: colours may vary according to your screen settings.

River - Article passport

A woven microsuede with leather print and a nice and full handfeel.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	microsuede woven
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100%PES
Composition backside	100%PES
Bonding	fleece
Statistic code	60019200
Dyeing method	piece dyed
Available colours	21
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	34.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	4		min. 4	min.5	C
	dark colours	CTL	grade	4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	2-3	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/C
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 40
Material weight in grams per linear meter	± 546

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.087	376	min. 350	min. 400	A/C
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	49,5	38,9	min. 25	min. 30	A/B
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	13,3	21,5	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	-0,4	n/a	n/a	A/A

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl

okt 2026