Sino



Textaafoam | Comfort
Expect what's next in furniture fabrics

Sino

This super soft quality is a proud member of our Comfort collection. A collection that consists only of soft, voluminous and elegant upholstery fabrics.

Sino is proud to present itself as super soft and incredibly comforting. This piece dyed fabric is woven on a jacquard loom and has an elegant structure. The chenille yarns create this super soft handfeel, kindly note that seat depression and shading can appear during use. This can be minimized by brushing the Sino regularly with a furniture or clothing brush.

The colours are as soft as the touch of the fabric itself. The fact that the fabric is 100% polyester and machine-washable at 30 degrees Celsius* makes it easy to maintain. Both loose and fitted upholstery are possible, so you can choose either way.

Sino's softness will comfort you at any time.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam originals *Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside n/a
/ chenille jacquard

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



army 14



ecru 102



eucalyptus 193



graphite 66



iceblue 43



ivory 101



lightgrey 60



liver 10



magnolia 160



maize 22



natural 01



pale 200

Please note: colours may vary according to your screen settings.



plumb 168



thyme 206



wood 108

Please note: colours may vary according to your screen settings.

Sino - Article passport

A super soft and incredibly cozy jacquard woven and piece dyed beauty.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille jacquard	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	n/a	
Coating	transparent	
Statistic code	54075200	
Dyeing method	piece dyed	
Available colours	15	
Packaging	bubble wrap	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 140
Roll length in meters	± 35
Material weight in grams per linear meter	± 620

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	689	935	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	137,5	139,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	2,2	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl

okt 2026