Spider



Textaafoam | Avantgarde
Expect what's next in furniture fabrics

Spider

Our Spider is a chenille jacquard woven quality and part of our Avantgarde Collection. A collection with creative, modern, trendy and coloured patterns & structures.

This yarn dyed textile has been woven on a jacquard loom, to create this special marble aspect. With Spider you get an on trend, soft upholstery fabric with chenille texture.

This trendy upholstery quality fits great to any type of furniture and is perfect combinable with many other Textaafoam originals. A nice combination can be made with articles such as Challenger, Juke, Wing or Loft.

Spider can be applied widely and is easily upholstered on both fitted and loose-fitting upholstery. This trendy and rich article is machine-washable at 30 degrees Celsius*.

Kindly note that during usage, a certain woolliness/ hairiness can appear, this is a product related property and it can easily be taken away with a pilling machine. Note that the usage of a pilling machine has no further influence of the durability of Spider.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam originals *Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside n/a
/ chenille jacquard

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



caramel 16



copper 126



cream 02



denim 153



graphite 66



hazel 96



jungle 207



lightgrey 60



mustard 06



natural 01



plumb 168



steel 149

Please note: colours may vary according to your screen settings.



taupe 12



thyme 206

Please note: colours may vary according to your screen settings.

Spider - Article passport

A very soft yarn dyed article with an all-over woven marble aspect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille jacquard	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	n/a	
Coating	transparent	
Statistic code	58013300	
Dyeing method	yarn dyed	
Available colours	14	
Packaging	bubble wrap	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	30.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	A
	middle colours	CTL	grade	5		min. 4	min.5	A
	dark colours	CTL	grade	5		min. 4	min.5	A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 140
Roll length in meters	± 35
Material weight in grams per linear meter	± 610

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.937	484	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	170,6	65,3	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,8	2,2	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	-0,4	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl

okt 2026