Unit



Textaafoam | Timeless
Expect what's next in furniture fabrics

Unit

Unit is a soft and elegant flatwoven upholstery fabric in our Timeless Collection. This collection features all our creative essentials. Fabrics that offer the best value for money and suit every style all year round.

Woven on an air jet loom, piece dyed and available in an extensive colour range. Unit features a fine flat structure with a soft mélange appearance in tone-on-tone colours. The gentle texture adds a quiet depth to any piece of furniture while maintaining a calm and timeless look.

The composition is 85% polyester and 15% cotton. The blend offers a natural handfeel with the benefits of easy maintenance and strength. Suitable for a wide variety of furniture styles—fitted, buttoned, and loose-fitting.

During use, a certain hairiness may appear. Kindly note that this has no influence on the durability of the textile and can be taken away with a pilling machine.

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.


Textaafoam originals *Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition


/ faceside 85%PES 15%CO
/ backside 100%PES
/ flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67




aqua 143



azure 144



beige 05



black 61



blossom 166




brown 15




darkblue 48



denim 153



darkgrey 68



lava 165



lightgrey 60

Please note: colours may vary according to your screen settings.



magnolia 160



mocca 13



pistachio 52




plumb 168



sand 03



sesame 113



steel 149



stone 181



taupe 12



turtle 88

Please note: colours may vary according to your screen settings.

Unit - Article passport

A fine flat structured article with a soft mélange appearance in tone-on-tone colours.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	85%PES 15%CO	
Composition backside	100%PES	
Bonding	non-woven	
Statistic code	55151190	
Dyeing method	piece dyed	
Available colours	22	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	35.000		min. 16.000	min. 25.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4-5		min. 4	min.5	B-C
	middle colours	CTL	grade	4-5		min. 4	min.5	B-C
	dark colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 143
Roll length in meters	± 40
Material weight in grams per linear meter	± 529

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.476	1.444	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	217,4	176,0	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,0	3,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	45,5	52,6	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	1,2	1,2	n/a	n/a	A/A

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl

okt 2026