



Shout



**Textaafoam** | Timeless  
creativity in fabrics



# Shout

A new flatwoven quality in the Textaafoam Timeless Collection is our article Shout. The timeless collection represents all our creative essentials.

Fabrics that offer the very best value for money and suit every style all year round. A rough construction in a strong multicoloured aspect is what our customers wished for. Our development department developed: Shout!

Shout has a tough and cool appearance while feeling nice and soft to the hand. This article is durable, strong and washable at the same time. A needle punch coating brings a light woolly look and feel and it will suit all different types of furniture perfectly.

Shout consists of 3 different synthetic yarn types and is yarn dyed, this quality has a stable colour consistency. Shout is available from stock in a nice range of commercial and trendy colours.

*Textaafoam <sup>originals</sup> Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

## Composition

/ Faceside 53%PES 27%PAC 20%PP  
/ Polyester polyacrylic polypropylene  
flatweave

## Suitable for


Sofa's, beds, chairs with fitted  
and loose fitting upholstery




beige 05




steel 149




zinc 167




bisque 91




grey 65




darkgrey 68




liver 10




plumb 168




anthracite 67



brown 15




wenge 192




royalblue 47



sun 133



bronze 116



scarlet 141



olive 53

## Shout - Article passport

Fabric with a multi-coloured aspect and a rough construction for a rich appearance.

Available from stock in a wide range of contemporary and commercial colours.

### Product characteristics

Productgroup	Polyester polyacrylic polypropylen flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	53%PES 27%PAC 20%PP
Statistic Code	58013600
Coating	needle punch
Dyeing method	yarn dyed
Available colours	16

### Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	55.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	bright colours	CTL	grade	5		min. 4	min. 5	A
	middle colours	CTL	grade	5		min. 4	min. 5	A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	bright colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
Ignitability	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part 1. Ignition source 0: cigarette	CTL		passed				






### Processing specifications

Minimum workable width in centimeters	± 138	
Roll length in meters	± 40	
Material weight in grams per linear meter	± 567	






Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.350	781	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	235,6	177,9	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	2,7	5,0	max. 5	max. 4	A/B
Chemical substances	REACH	Centexbel		passed				

### Cleaning specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	- 2,4	- 0,6	n/a	n/a	B/A

We recommend to immediately place the cover back to the piece of furniture slightly damp after washing

**Textaafoam**  
creativity in fabrics

Textaafoam b.v.  
La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934  
F +31(0)13 534 7586  
E info@textaafoam.nl  
www.textaafoam.nl