


Aston





















Aston

The Textaafoam Skins Collection features only the best alternatives for real leather in the market, like this special developed microsuede knitted textile.

Our product development team wanted to create an alternative for a real aniline-leather. After several steps we are proud to inform you that this has been realised, this textile has been created together with an important factory / partner for Textaafoam, the result is an elegant and thick new microsuede and the name Aston.

Developing a new soft and innovative finish has made it possible that this comfortable leather look and structure can be created. Aston has a light tone-in-tone print, slightly shiny and will make the furniture or bed look extremely elegant.

Aston is machine-washable at 30 degrees Celsius*, also damp and dirt resistant, therefor easy for usage and maintenance. Kindly note that during use the surface will become a bit more roughened, this has no further influence on the durability of this textile.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.
- Dirt and damp prevention treatment applied.

Textaafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 100%PES / backside 100%PES / microsuede knitted

Suitable for



Please note: colours may vary according to your screen settings.



Aston - Article passport

An elegant and thick microsuede with a leather aspect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics									
Productgroup	microsuede knitted								
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery								
Composition faceside	100%PES								
Composition backside	100%PES								
Bonding	fleece								
Statistic code	60019200								
Dyeing method	piece dyed								
Available colours	17							-	
Packaging	bubble wrap							-	

Durability specifications										
Test		Executed by laboratory:		Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09		
				Dry	Wet	DGM	DGM+			
Abrasion resistance - yarn breakage		DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	70.000		min. 8.000	min. 16.000	С	
Pilling		DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	В	
Colour fastness to light		DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5								
		light colours	CTL	grade	3-4		min. 4	min.5	С	
		middle colours	CTL	grade	3-4		min. 4	min.5	С	
		dark colours	CTL	grade	3-4		min. 4	min.5	С	
Colour fastness to rubbing		DIN EN ISO 105-X12:2016-11								
		light colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A	
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
lgnitability (cigarette test)		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed					

Processing specifications								
Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 690							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.188	710	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	77,8	54,1	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,6	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	19,4	25,1	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		pa	ssed			
	Oeko-Tex, product class II	Centexbel		cer	tified			

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,2	0,0	n/a	n/a	A/A






























creativity in fabrics

Textaafoam b.v. La Défense 11 | 5026 SC Tilburg P.O. Box 12 | 5050 AA Goirle The Netherlands

T+31(0)13 534 5934 F+31(0)13 534 7586 E info@textaafoam.nl www.textaafoam.nl