

Parq









Parq

The Textaafoam Skins Collection features great looking leather alternatives, quality Parq is another example of this. An upholstery fabric with an elegant leather-look and a silky and smooth touch, just like real leather.

This knitted microfiber has been dyed, printed and finished with a special foil. Together with a heavy laminated fleece backing, it gives the upholstered furniture an amazing look.

Just like leather, the surface / appearance can a bit change during use, this is depending on how the furniture is used and cared for. Scratches and sharp objects can change the aspect of the surface, like a more roughened look, this is property of these qualities and it has no further influence on the durability of this textile.

Available from stock in a nice contemporary and commercial colour-line of 10 different colours.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 100%PES / backside 100%PES / microsuede knitted


Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



espresso 123

graphite 66



grey 65



liver 10



plumb 168



sepia 176



taupe 12

Please note: colours may vary according to your screen settings.

		i		
Parq - Article passport				
Article with an elegant leather-look and a silky and smoot	th touch, just like real leather.		-	
Available from stock in a wide range of contemporary and	d commercial colours.			
Product characteristics				
Productgroup	microsuede knitted			
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery			
Composition faceside	100%PES			
Composition backside	100%PES			
Bonding	fleece			
Statistic code	60053700			
Dyeing method	piece dyed			
Available colours	10			
Packaging	bubble wrap			

Durability specifications											
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09			
	,		, F	Dry	Wet	DGM	DGM+				
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	55.000		min. 8.000	min. 16.000	В			
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	В			
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5										
	light colours	CTL	grade	4		min. 4	min.5	С			
	middle colours	CTL	grade	3	3-4		min.5	с			
	dark colours	CTL	CTL grade 3-4		,-4	min. 4	min.5	С			
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11	DIN EN ISO 105-X12:2016-11									
	light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A			
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A			
	dark colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A			
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	СТL		passed							

Processing specifications								
Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 616							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.037	570	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	49,8	33,4	min. 25	min. 30	A/B
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,5	1,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	13,8	17,5	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		pa	sed		•	•
	Oeko-Tex, product class II	Centexbel		certified				

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,1	0,0	n/a	n/a	A/A
P 🖾 🗟 🗟	- We recommend to wash the cover in	nside out and immedia	tely place the co	ver back to the pie	ce of furniture, sligh	tly damp, after was	hing.	

OEKO-TEX®

REACH





Textaafoam b.v. La Défense 11 | 5026 SC Tilburg P.O. Box 12 | 5050 AA Goirle The Netherlands

T +31(0)13 534 5934 F +31(0)13 534 7586 E info@textaafoam.nl www.textaafoam.nl