



Zegna



OEKO-TEX®
CONFIDENCE IN TEXTILES



Textaafoam  | Skins
creativity in fabrics



Zegna

Our Skins Collection features only the best leather alternatives in the market, like this new quality Zegna.

The ambition was to develop a strong, durable and easy-to-clean upholstery fabric, which is suitable for all types of upholstery. It was a challenging ride, but after several steps we realized this new 100% polyester textile, which has the touch like leather.

The production process is rather unique, a soft new finish provides Zegna a comfortable and natural hand feel, but also an elegant and slightly shiny look. Please note that during use this aspect will become a bit more roughened / visible, this has no further influence on the durability of this quality.

Zegna is machine-washable at 30 degrees, this finish also provides a damp and dirt resistancy, therefore liquids and other substances have hardly any chance. Furthermore, this suede is laminated with a thick backing, available from stock in a commercial and trendy colour. Zegna will lift up the furniture for sure.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.
- Dirt and damp prevention treatment applied.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%PES
/ microsuede knitted

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67



army 14



beige 05



burgundy 34



clay 84



cognac 28



ecru 102



espresso 123



hunter 156



ivory 101



latte 211




liver 10


Please note: colours may vary according to your screen settings.



mustard 06



onyx 169



plumb 168



sand 03



taupe 12



thyme 206

Please note: colours may vary according to your screen settings.


Zegna - Article passport

A strong, durable and easy-to-clean upholstery fabric with a touch like leather.
Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	microsuede knitted	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	100%PES	
Bonding	fleece	
Statistic code	60019200	
Dyeing method	piece dyed	
Available colours	18	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	35.000		min. 8.000	min. 16.000	C
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	4		min. 4	min.5	C
	dark colours	CTL	grade	4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
gnitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 30							
Material weight in grams per linear meter	± 635							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	920	885	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	40,7	49,8	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	1,0	1,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	16,6	20,2	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,8	-0,8	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.
- Dirt and damp prevention treatment applied.



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl